

**CAIRO UNIVERSITY
FACULTY OF ENGINEERING
PUBLIC WORKS DEPARTMENT**

**Structural Design of Highways
(Part II-A)
Asphalt Pavement Materials**

Handout (4) : Aggregates

Lecturer: Dr. Gamal S. Darwish

3- Aggregates

3-1 Aggregate Sources and Types

3-2 Desirable Properties of Aggregates

3-3 Gradation Requirements & Aggregate Blending


3-4 Bases and Subbases

Aggregates:

- It is a key component of highway pavement from the W.S to the Subgrade.
 - Portland cement concrete: 60 to 75% volume and 79 to 85% weight
 - Asphalt concrete: 80% volume and 92 to 96% weight
 - Base courses
- Many sources, many types, diverse properties.
- Improper aggregate selection and use = Pavement failure.


So, it's important to study the properties of aggregates

3-1 Aggregate Sources and Types:



- 1- Dense (well) graded agg.
- 2- Open graded Agg.
- 3- Gap graded Agg.
- 4- one-size Agg.

- (Surface layer mixes)
 (Binder layer or surface drainage mixes)
 (Mixes with rich asphalt cement)
 (Macadam or surface treatment)



Dense Gradation

Uniform Gradation

Open Gradation

Gap Gradation

gradations

o

3-1 Aggregate Sources and Types:

1) Natural :

- Excavation —→ removal of overburden —→ quarrying
(digging, cutting, blasting)
- Sand, Gravel, rocks :
- Non- processed sand & Gravel
- Processed: Granite, Basalt, Limestone, Dolomite, ...etc.
- Processing:
Quarrying (digging, cutting, blasting) —→ crushing —→ sieving
& dirt removing —→ stock piling —→ use in construction

2) Manufactured (artificial) : blast furnace slag (light weight agg.)

3-2 Desirable Properties of Aggregates

1- Cleanliness:

Free from organic materials, Clay dust or any foreign substances.

2- Toughness:

Resistance to abrasive wear during processing, placing, and compaction.

3- Soundness:

Durability measures, resistance to weather action.

4- Particle shape:

Minimum flat and elongated particles


5- Surface texture:

Rough surface texture provides better friction between particles.


6- Absorption:

more absorption would improve adhesion between agg. And asphalt.


Particle Shape




(a) Angular




(b) Rounded



(c) Flaky



(d) Elongated



(e) Flaky and elongated

Laboratory Tests for Aggregate Properties

<u>Agg. Property</u>	<u>Test Used</u>
Cleanliness	Washed sieve size Analysis or sand-equivalent test.
Toughness	Loss Angles Abrasion Test.
Soundness	Magnesium Sulphate Test (Soaking-Drying cycles)
Particle shape	% Flat and Elongated particles.
Absorption	Absorption test.
Affinity for Asphalt	Marshal relative Stability Test.
Specific Gravity	Specific gravity test
Strength	California Bearing Ration (CBR) test

Desirable Properties of Aggregates

a) Affecting strength (Load):

1- Strength & Toughness :

- Resist loads (construction or traffic) without breakdown or degradation
- Open-graded tend to break easily

Tests :

- Crushing resistance —————> Los Angeles Test (metal drum, 12 steel balls, rotate 500 times @ 32 rpm, impact, % pass # 12 = LA abrasion)
- Load carrying —————> CBR Penetration test. (California bearing Ratio)

b) Affecting Durability (Weathering):

1- Hydrophobic character:

- Hydrophilic (water loving) agg. —→ Bit. Displaced by water —→ stripping
- Hydrophobic (water hating) agg. —→ Good adhesion between agg & Bit.

Tests : Immersion compression test (asphalt mix)

dry sample (store in air) —→ compression

soak in water —→ compression. Reduction in strength

2- Soundness : Disintegration under the effect of weathering (water, freez)

Test: Crumbling under soaking / overdrying cycles.

LA Abrasion (ASTM C131)

- Step 1: prepare specific agg gradation

Passing	Retained	A	B	C	D
37.5 mm	25.0 mm	1,250	---	---	---
25.0 mm	19.0 mm	1,250	---	---	---
19.0 mm	12.5 mm	1,250	2,500	---	---
12.5 mm	9.5 mm	1,200	2,500	---	---
9.5 mm	6.3 mm	---	---	2,500	--
6.3 mm	4.75 mm	---	---	2,500	---
4.75 mm	2.36 mm	---	---	---	5,000
No. Steel Balls		12	11	8	6

LA Abrasion

- Step 2: Rotate for 500 revolutions at 30 to 33 rpm's



LA Abrasion (ASTM C131)

- Step 3. Empty cylinder, remove balls, and make preliminary separation of agg on 1.70 mm (No. 12) sieve



Steel balls need to
be removed

LA Abrasion (ASTM C131)


- Step 4: Wash material retained on No. 12 sieve, dry to constant weight, and determine dry (cooled) mass
- % Loss = $\frac{(\text{original wt} - \text{final wt})}{\text{original wt}} \times 100$

- 2- Particle shape :
 - Mechanical Resistance to displacement via interlocking
 - Angular shapes are better than elongated or thin shapes.
- 3- Surface texture : Rough texture resists skidding and gives good friction
- 4- Porosity: - low porosity is needed for better adhesion with bitumen
 - No or high porosity is not good

Tests : % water absorption using immersion test.

3-3 Gradation Requirements & Aggregate Blending

- Dense-graded
- Open-graded
- One-sized



Aggregate Gradation Type

- 1- Dense (well) graded agg.
- 2- Open graded Agg.
- 3- Gap graded Agg.
- 4- one-size Agg.


Application

- (Surface layer mixes)
- (Binder layer or surface drainage mixes)
- (Mixes with rich asphalt cement)
- (Macadam or surface treatment)

Types of Gradations


- **Uniformly graded**

- Few points of contact
- Poor interlock (shape dependent)
- High permeability




- **Well graded**

- Good interlock
- Low permeability



- **Gap graded**

- Only limited sizes
- Good interlock
- Low permeability



Base and Subbase Materials

3-4 Base and Subbase Materials

Base Layer : is granular material treated or untreated.


Treated : Stabilized or cemented with lime, Portland cement, asphalt cement,.....etc.

Untreated: Only aggregate (without additives).


Both base and subbase materials are characterized by:

- a) Soil Classification methods.
- b) Aggregate Evaluation Tests (LOA, Soundness,etc).
- c) California Bearing Ratio (CBR).
- d) Plate Bearing Test.


Types of Base Course



(Dust interlock and Friction)



(Friction + Cementation)



(Cementation)

Crushed Rock multi-layers
Los Angeles Abrasion $\nless 50\%$

Requirements for Granular Sub-Base Layer :

- **Gradation Requirements**
- **L.L. $\nless 30$ %**
- **P.I. $\nless 8$ %**
- **CBR $\nless 25$ % for access & local Roads and $\nless 40$ % for main Roads with no Swelling**
- **Crumbling for coarse aggregates (retained on sieve # 4) $\nless 10$ %**
- **Absorption $\nless 10$ %**
- **No organic materials or other dirts.**

Requirements for Granular Base Course :

- **Gradation Requirements**
- **LOA $\nless 50$ % (after 500 cycle).**
- **L.L. $\nless 25$ %**
- **P.I. $\nless 6$ %**
- **CBR $\nless 60$ % for access & local Roads and $\nless 80$ % for main Roads with no Swelling**
- **Crumbling for coarse aggregates (retained on sieve # 4) $\nless 5$ %**
- **Absorption $\nless 10$ %**

الباب الثالث

الكود المصري لأعمال الطرق الحضرية والبلدية
الجزء التاسع : اشتراطات تنفيذ أعمال الطرق داخل وخارج المدن

٣-٢ اشتراطات اعمال انشاء طبقات الأساس المساعد والأساس

٣-٢-١ طبقات الأساس المساعد:

تنفذ طبقة الأساس المساعد من مواد حصوية متدرجة مخلوط بها المواد الرابطة اللازمة بحيث تشكل هذه المواد كلها بعد خلطها جيداً وفرشها على سطح الطريق السابق اعداده واضافة المياه اللازمة اليها ودمكها كطبقة متجانسة متماسكة حسب الاشتراطات والمواصفات وطبقاً للميول والقطاعات الطولية والعرضية الميمنة بالرسومات المرفقة بنقطة الشروط الخصوصية.

٣-٢-١-١ المواد:

- تتكون المواد من حصي غليظ ورفيع والمواد الرابطة اللازمة لملء الفراغات والتي تكون في مجموعها خليطاً متدرجاً متجانساً ومطابقاً للمواصفات.
- يجب ألا يزيد أقصى حجم عن ٣ بوصة وبحيث لا يتعدى ٣/٢ سمك الطبقة بعد دمكها وفي حالة وجود أحجار يزيد حجمها عن أقصى حجم فيلزم استبعادها في مصادرها قبل التوريد الى الموقع او فصلها بالهز او إعادة تكسيدها الى الأحجام المطلوبة.

٢-١-٢-٢ تدرج المواد:

يجب أن يتفق تدرج المواد المورد لإثشاء الطبقة مع أحد التدرجات الآتية:-

النسبة المئوية للعار من المنخل			حجم المنخل
التدرج (ج)	التدرج (ب)	التدرج (أ)	
		١٠٠	٣ بوصة (٧٥ مم)
	١٠٠	١٠٠ - ٩٠	٢,٥٠ بوصة (٦٢,٥٠ مم)
١٠٠	١٠٠ - ٩٠	٩٥ - ٨٠	٢ بوصة (٥٠ مم)
١٠٠ - ٩٠	٩٥ - ٨٠	٨٥ - ٦٥	١,٥٠ بوصة (٣٧,٥٠ مم)
٩٠ - ٧٠	٨٥ - ٦٥	٧٥ - ٥٥	٠,٧٥ بوصة (١٩ مم)
٧٥ - ٤٠	٧٠ - ٣٥	٦٠ - ٣٠	رقم ٤ (٤,٧٥ مم)
٢٠ - صفر	١٥ - صفر	١٠ - صفر	رقم ٢٠٠ (٠,٠٧٥ مم)

الباب الثالث

الكود المصرى لأعمال الطرق الحضرية والخلوية

الجزء التاسع : اشتراطات تنفيذ أعمال الطرق داخل وخارج المدن

٣-٢-١-٣ خصائص المواد:

- يمكن توريد المواد بما يتفق مع أكثر من تدرج واحد او طبقا لما ينص عليه دفتر الشروط الخاص بالمشروع على ان يتم انشاء مسافة طولية كاملة من كل تدرج على حده لا يقل طولها عن واحد كم بعد أخذ موافقة المهندس المشرف.
- يجب الا يزيد نسبة المواد القابلة للتفتت في الماء من المواد المحجوزة على المنخل رقم (٤) عن ١٠ (عشرة في المائة) بالوزن ولا يزيد نسبة الامتصاص عن (عشرة في المائة) ١٠.
- يجب الا يقل نسبة تحمل كاليفورنيا لعينة يتم دمكها طبقا للدمك المعدل (بروكتور) وغمرها في الماء لمدة اربعة ايام عن ٤٠% للطرق الرئيسية والهامة و ٢٥% للطرق الفرعية والمحلية مع خلوها من الانتفاخ طبقا للاختبار القياسى.
- يجب الا يزيد حد السيولة عن ٣٠% ومجال اللدونة عن ٨%.

٣-٢-٢-٢ - خواص المواد

(أ) المواد المطلوبة لطبقة الأساس

تتكون المواد المطلوبة لطبقة الأساس من ناتج التكسير أو خليط منها تكون في مجموعها مخلوطا متدرجا مطابقا للمواصفات.

(ب) يجب مراعاة الآتي في إستخراج المواد من المحاجر:

- لايسمح بنقل المواد من المحاجر إلا بعد إعتماد المحجر من المهندس المشرف مع متابعه صلاحية المواد من المحجر بصفة دائمة.
- يقوم المقاول بكشف المحجر وذلك بتنظيف الموقع من الأشجار والحشائش والجذور وجميع المواد الضارة ثم كشف الطبقة العليا منه والمعرضة لعوامل التعرية والتي غالبا ماتحوى أثرية أو مواد عضوية أو مواد متفتتة أو ضارة وذلك بمسطح كاف يزيد عن المسطح المطلوب حفره لمنع إنبهار الأثرية وإختلاطها بمواد المحاجر بعد تشوينها.
- المقاول مسئول عن كيفية نقل المواد من مصادرها إلى موقع العمل.
- يجب أن تكون المواد المنقولة من المحاجر متجانسة ونظيفة وخالية من أى شوائب أو مواد غريبة مع مراعاة عدم فقدان أى مكون من مكوناتها أثناء النقل.
- يجب أن لاتقل نسبة تحمل كاليفورنيا بعد الغمر فى الماء عن ٨٠% وذلك بالنسبة للطرق الحرة والرئيسية ولاتقل عن ٦٠ % بالنسبة للطرق الفرعية والثانوية والمحلية أو طبقا لما هو وارد فى الشروط والمواصفات الخاصة للمشروع.

(ج) المواد الغليظة:

- تتكون المواد المحجوزة على منخل رقم (١٠) من حصويات صلبة قوية سواء أكانت سائبة أو جيرية.
- نسبة الفاقد في جهاز لوس أنجلوس لا يزيد عن ٥٠ طبقا للاختبار القياسي.
- يجب ألا تزيد نسبة المواد القابلة للتفتت في الماء من المواد الغليظة المحجوزة على منخل رقم ٤ عن ٥% من وزنها.
- عدد عمر عينة من الطبقة في أقصى كثافة جافة طبقا للمعدن ينبغي خلوها تماما من الإنقماش الحر طبقا للاختبار القياسي.
- يجب ألا تزيد نسبة الإمتصاص بالمياه بعد ٢٤ ساعة عن ١٠% للمواد الغليظة.

الباب الثالث

لكود المصري لأعمال الطرق الحضرية والبلدية
الجزء التاسع : اشتراطات تنفيذ أعمال الطرق داخل وخارج المدن

(د) المواد الرقيقة: المارة من منخل رقم ١٠:

- تتكون من رمال طبيعية أو ناتج تكسير كسارات أو خليط منهما.
- يجب ألا يزيد الجزء المار من منخل رقم ٢٠٠ عن ثلثي الجزء المار من منخل رقم ٤٠.
- لدونة الجزء المار من منخل رقم ٤٠:
 - حد السيولة أقصى ٢٥%
 - مجال اللدونة أقصى ٦%

(هـ) يجب أن تكون جميع المواد خالية من المواد العضوية والتجمعات الطينية.

٣-٢-٢-٣ - تدرج المواد:

تكون مواد طبقات الأساس متدرجة طبقاً لأحد التدرجات التالية:

النسبة المئوية للمار من المنخل			حجم المنخل
التدرج (جـ)	التدرج (ب)	التدرج (أ)	
---	---	١٠٠	٥٠ ميليمترا (٢ بوصة)
---	١٠٠	١٠٠-٨٠	٣٧,٥ ميليمترا (١,٥ بوصة)
١٠٠	٩٥-٧٠	٨٥-٥٥	٢٥ ميليمترا (١ بوصة)
١٠٠-٧٠	٨٥-٥٥	٨٠-٥٠	١٩ ميليمترا (٣/٤ بوصة)
٦٥-٣٥	٦٠-٣٠	٦٠-٣٠	٤,٧٥ ميليمترا (رقم ٤)
٣٠-١٥	٣٠-١٠	٢٥-١٠	٠,٤٢٥ ميليمترا (رقم ٤٠)
١٥-٥	١٠-٣	١٠-٣	٠,٠٧٥ ميليمترا (رقم ٢٠٠)